

AMENDMENT TO THE CLAIMS
LISTING OF THE CLAIMS

Claims 1 – 6 CANCELED

Claims 7 – 19 ORIGINAL

Claims 20 – 24 CANCELED

FAX RECEIVED
AUG 06 2003
GROUP 1700

AMENDMENT TO THE CLAIMS

TEXT OF CLAIMS CURRENTLY UNDER EXAMINATION

Claims 1 – 6

canceled. ✓

7. (original) A process for making a glove comprising:
- (a) immersing a glove former in an aqueous polymer composition;
 - (b) immersing said glove former in a coagulant solution, to produce a coated former;
 - (c) immersing the coated former into a rubber latex to coat the former with said latex;
 - (d) chlorinating the latex on said coated former;
 - (e) curing the chlorinated latex on said coated former; and
 - (f) removing the finished glove from the former.

8. (original) The process of claim 7 wherein steps a) and b) occur as a single step by immersing a glove former in a coagulant solution comprising said aqueous polymer composition.

9. (original) The process of claim 7 wherein said polymer comprises a water-borne polymer having a Tg of greater than -10°C formed from at least one hydrophobic monomer, and at least one hydrophilic monomer.

10. (original) The process of claim 7 wherein the chlorinating of the latex coated former comprises immersing said former in a solution comprising chlorine and water.

11. (original) The process of claim 7 wherein said aqueous chlorine solution contains from 500 to 15,000 ppm of chlorine.
12. (original) The process of claim 11 wherein said aqueous chlorine solution contains from 1,000 to 10,000 ppm of chlorine.
13. (original) The process of claim 7 wherein said chlorination of the latex occurs in-line.
14. (original) A process for making a glove comprising:
- (a) Immersing a glove former in an aqueous polymer composition;
 - (b) immersing said glove former in a coagulant solution, to produce a coated former;
 - (c) immersing the coated former into a rubber latex to coat the former with said latex;
 - (d) curing the latex on said coated former;
 - (e) chlorinating the latex on said coated former; and
 - (f) removing the finished glove from the former.
15. (original) The process of claim 14 wherein steps a) and b) occur as a single step by immersing a glove former in a coagulant solution comprising said aqueous polymer composition.
16. (original) The process of claim 14 wherein said polymer comprises a water-borne polymer having a Tg of greater than -10°C formed from at least one hydrophobic monomer, and at least one hydrophilic monomer.

17. (original) The process of claim 14 wherein the chlorinating of the latex coated former comprises immersing said former in a solution comprising chlorine and water.

AI

18. (original) The process of claim 14 wherein said aqueous chlorine solution contains from 500 to 15,000 ppm of chlorine.

19. (original) The process of claim 14 wherein said chlorination of the latex occurs in-line.

Claims 20 – 24 canceled
